

UV Tracer

A light viscosity, lithium soap thickened, polyolester grease
Intended for electrical contact and small precision bearing applications.

Ford: WSS-M1C255-A1

Lubricant Properties		Typical Value	Test Method
Recommended Service Range (°C)		-54 to 150	
Thickener		Lithium Soap	
Base Oil	Type	Ester	
	Kinematic Viscosity	100°C	4.1 cSt
		40°C	18.5 cSt
	Viscosity Index		125
	Flash Point	°C	256
	Pour Point	°C	-67
Typical Properties of the Grease		Typical Value	Test Method
Color, Appearance		Tan, Smooth	
Penetration (1/10 mm)	NLGI Grade	2	ASTM D-217
	Unworked	267	ASTM D-217
	Worked	60X	281
Density		25°C	0.91 g/cm ³
Oil Separation	24 hour(s)	100°C	4.6
			FTM 791, Method 321.2
Evaporation	24 hour(s)	100°C	0.3 %
			NYE CTM

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product.

(1901)