

A PTFE thickened, heavy viscosity, completely fluorinated grease for use in high temperature applications exposed to fuels or aggressive chemicals. It possesses excellent thermo-oxidative stability and low vapor pressure characteristics.

Lubricant Properties		Typical Value	Test Method
<b>Recommended Service Range (°C)</b>		-65 to 250	
<b>Thickener</b>		PTFE	
<b>Base Oil</b>	Type	Perfluoropolyether	
<b>(Uniflor 8920)</b>	Kinematic Viscosity	100°C	40 cSt
		40°C	135 cSt
		-40°C	4823 cSt
	Viscosity Index		334
Flash Point	°C	Non-Flammable	ASTM D-92
Pour Point	°C	-65	ASTM D-97
Typical Properties of the Grease		Typical Value	Test Method
<b>Color, Appearance</b>		White, Smooth	
<b>Penetration (1/10 mm)</b>	Worked	60X	295
	Unworked		269
	NLGI Grade		2
<b>Density</b>		25°C	1.83 g/cm <sup>3</sup>
<b>Oil Separation</b>	24 hour(s)	100°C	4.7
<b>Evaporation</b>	24 hour(s)	200°C	0.1 %

The typical properties shown on this product data sheet should not be used as a basis for preparing specifications. Refer to our product SDS for detailed safety information on this product. (1903)